

Noweed Weedmatting Physical Properties

Property	Test Method	Premium 110gsm (Mean Roll Values)
Material		Polypropylene
Colour		Black
Mass		110 g/m2
Construction		96 x 44/10cm
Tensile Strength (wide width)	AS3706.2	22/18 kN/m
Grab Tensile Strength	AS3706.2	750/650 N
Elongation	AS3706.2	17/17
Trapezoidal Tear Strength	AS3706.3	225/225 N
CBR Burst	AS3706.4	2.6 kN
Flow Rate (under 100 mm head)	AS3706.9	15 litres/m2/sec
Effective Opening Size (EOS)	AS3706.7	150 mu
UV Resistance	AS3706.11	> 95% after 500 hours

The data in this specification is subject to change and is not intended as a warranty or guarantee.



Permathene Australia
9/ 8 Gladstone Road, Castle Hill
Sydney, NSW 2154
Tel: (02) 7804 2656
www.permathene.com.au