

Noweed Weedmatting Physical Properties

Property	Test Method	Premium
Material		Polypropylene
Colour		Black
Mass		110 g/m ²
Construction		96 x 44/10cm
Tensile Strength (wide width)	AS3706.2	22/18 kN/m
Tensile Strength (grab)	AS3706.2	750/650 N
Elongation	AS3706.2	17/17 %
Trapezoidal Tear Strength	AS3706.3	225/225 N
CBR Burst	AS3706.4	2.6 kN
Flow Rate (under 100 mm head)	AS3706.9	15 litres/m ² /sec
Effective Opening Size (EOS)	AS3706.7	150 µ
UV Resistance	AS3706.11	> 95% after 500 hours

The data in this specification is subject to change and is not intended as a warranty or guarantee.



Permathene Australia
28 Mount Erin Road, Campbelltown 2560
Tel: (02) 4620 7785
www.permathene.com.au