



## Flexible Polyethylene geomembrane

## Description

Permaflex<sup>™</sup> fPE is a highly flexible geomembrane designed as a replacement for flexible polypropylene where chemical resistance to chlorine and acids is required. Permaflex fPE has excellent physical properties and UV resistance.

## Applications

- **Tanks:** Lining membrane for timber, concrete and metal tanks and secondary lining for preventing pollution in case of leakage or chemical spill.
- Pond and Dam Lining: For lining and liquid storage.
- Baffle Curtains: Suitable for WWTP turbidity barriers and baffle curtains.
- Biofilter Liners: Supply of factory fabricated rectangular liners.
- Damp Proofing: Superior Damp Proofing Membrane.

PROPERTY	METHOD	UNITS	0.5	0.75	1.0
Specific Gravity	EN ISO 1183	g/cm3	0.94	0.94	0.94
Thickness	EN 1849-2	mm	0.50	0.75	1.0
Tensile at Break MD	ASTM D6693IV*	MPa	25	25	25
Tensile at Break TD	ASTM D6693IV*	MPa	20	20	20
Elongation at Break MD	ASTM D6693IV** (- 5%)	%	1000	1000	1000
Elongation at Break TD	ASTM D6693IV** (- 5%)	%	1000	1000	1000
Puncture Resistance	ASTM D4833 (- 5%)	Ν	120	180	240
Tear Resistance	ASTM D1004 (- 5%)	Ν	35	52	70
Modulus of Elasticity	ASTM D6693 (± 10%)	MPa	100	100	100

\*Tensile Properties: 50mm/min, 33mm Gauge Length \*\* Tensile Properties: 50mm/min, 50mm Gauge Length Physical Properties: TUV Austria

Potable Water Tested: Meets AS/NZS 4020:2005 (certified as suitable for drinking water, aquaculture, etc).

This product meets the requirements of the New Zealand Building Code having a water vapour flow resistance of no less than 90MNs/g as tested in accordance to ASTM E96

Permathene Pty Ltd 9&11/ 8 Gladstone Road, Castle Hill, NSW 2154 Australia Tel: (02) 7804-2656 Toll Free: 1-800-60-80-95 Permathene Ltd. 404 Rosebank Rd Avondale Auckland New Zealand

Tel: (09) 968 8888